



TEST REPORT - FPM 90

COMP V9001b
MFR 8063

Complies to ASTM D2000 M3HK910 A1-10 B37 EF31

Colour BLACK

Temp range -20C TO +200C

		Requirements	Result
Properties	Hardness Shore A	90 +/-5	88
	Tensile Strength MPA	10	10.4
	Elongation %	100	132
	Specific Gravity		1.819
Compression Set	175C FOR 22 HRS	30	10
Fluid Resistance Test	Fuel C @ RT FOR 70 HRS		
	Change in Hardness, Max Points	+/-5	-3
	Tensile Strength Change %	-25	-6
	Elongation Change %	-20	+0.7
	Change in Volume %	0~-10	+5

Please note that these results are for reference purposes only and Supaseal makes no warranty, expressed or implied, that parts manufactured from this compound will perform satisfactorily in the customer's application. It is the customers responsibility to test and evaluate parts prior to use.

Tel: 01858 434141

Fax: 01858 434717 e-mail: sales@supaseal.co.uk